

電縫管

機械構造用炭素鋼鋼管
STKM 11A JIS G3445(1988)

kg/m

外径 mm \ 厚さ mm	1.0	1.2	1.6	2.0	2.3
6	.123				
7	.148				
8	.173				
9	.197				
9.5		.246			
10	.222	.260	.331		
11	.247				
12	.271	.320	.410		
12.7	.289	.340	.438		
14	.321				
15.9		.435	.564	.686	
19.1		.530	.690	.843	
22.2		.621	.813	.996	
25.4		.716	.939	1.15	1.31
28.6		.811	1.07	1.31	
31.8		.906	1.19	1.47	1.67
34		.971	1.28	1.58	1.80
35		1.00	1.32		
38.1		1.09	1.44	1.78	2.03
42.7		1.23	1.62		2.29
45			1.71	2.12	
48.6		1.40	1.85	2.30	2.63
50.8		1.47	1.94	2.41	2.75
54			2.07		
60.5			2.32	2.89	
63.5			2.44		
65			2.50		
76.3			2.95	3.66	

切断も承ります。

基準長さ 3.66m または 5